



Date of Issue: 5/9/2024 Report Number: 24-001060

Date Order Received: 04/29/2024

Revision Number:1

For the Account of: Zimmer & Rohde Germany

Zimmersmuhlenweg 14-18

61440 Oberursel

Germany

| Client's Identification: 10788 | 10788 |
|--------------------------------|-------|

CERTIFICATE OF TESTING

TEST PERFORMED: NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture – 2013; Fabric Cover Test and UFAC Fabric Classification Test Method – 1990; Standard Test Methods for Cigarette Ignition Resistance of Components of Upholstered Furniture ASTM E 1353-16 – Cover Fabric Test

TEST RESULTS

| Specimen | Char Length (in |
|----------|-----------------|
| 1 | 0.6 |
| 2 | 0.6 |
| 3 | 0.5 |

NOTES

Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity

ACCEPTANCE CRITERIA

- 1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 45 mm (1.75 in; ASTM states 1.8 in.) or less, the fabric is classified a Class I cover fabric.
- 2. If the vertical char of the test specimen greater than 45 mm (1.75 in.; ASTM states 1.8 in), the fabric is classified a Class II cover fabric.
- 3. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a Class II cover fabric.

| CONCLUSION | Based on the above Results and Acceptance Criteria, the item tested is: | |
|------------|---|--|
| | ⊠ Class I | |
| | ☐ Class II | |

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver

Authorized Signature Date Order Completed: 05/09/2024