



**Zimmer + Rohde GmbH**  
**Zimmersmühlenweg 14-18**  
**61440 OBERURSEL**  
**Germany**

**Your notice of**  
29-07-2024

**Your reference**

**Date**  
03-09-2024

## Analysis Report 24.04124.01


Required tests :

**EN 13773 (2003)**

Sample id	Information given by the client	Date of receipt
T2415334	10919	29-07-2024

Gina Créelle  
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



**Reference: T2415334 - 10919**

**Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.**


Date of ending the test 02-09-2024  
 Standard used EN 1101 (1995) + A1 (2005)  
 Product standard EN 13773 (2003)  
  
 Deviation from the standard -  
  
 Conditioning 20°C, relative humidity 65%  
 Testing atmosphere 25°C, relative humidity 65%  
  
 Dimension of the specimens 200 mm x 80 mm  
  
 Ignition Bottom edge

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

**Length**

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated  
 No ignition within 20 s



Width

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated  
 No ignition within 20 s

Minimum ignition time

No ignition within 20 s

**Reference: T2415334 - 10919**

**Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.**

Date of ending the test 02-09-2024  
 Standard used EN 13772 (2011)  
 Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%


The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

**Length**

	Front	Back	Back	Back
Severance 1 <sup>st</sup> thread	no	no	no	no
Severance 2 <sup>nd</sup> thread	no	no	no	no
Severance 3 <sup>rd</sup> thread	no	no	no	no
Time to sever 3 <sup>rd</sup> thread (s)	/	/	/	/
Destroyed length (mm)	130	135	130	130
Flaming debris	no	no	yes	no

**Width**

	Front	Back	Front	Front
Severance 1 <sup>st</sup> thread	no	no	no	no
Severance 2 <sup>nd</sup> thread	no	no	no	no
Severance 3 <sup>rd</sup> thread	no	no	no	no
Time to sever 3 <sup>rd</sup> thread (s)	/	/	/	/
Destroyed length (mm)	135	135	125	130
Flaming debris	no	no	no	no



Additional tests

Length

	Back	Back	Back
Severance 1 <sup>st</sup> thread	no	no	no
Severance 2 <sup>nd</sup> thread	no	no	no
Severance 3 <sup>rd</sup> thread	no	no	no
Time to sever 3 <sup>rd</sup> thread (s)	/	/	/
Destroyed length (mm)	125	125	125
Flaming debris	no	no	no

**Classification in accordance with EN**      **Class 1**  
**13773**