



Date of Issue: 5/20/2024 Report Number: 24-001110

Date Order Received: 05/01/2024

Revision Number:1

Zimmer & Rohde Germany Zimmersmuhlenweg 14-18 61440 Oberursel

Germany

Ociman

Client's Identification:	10006		
Client's Identification:	10996		

CERTIFICATE OF TESTING

TEST PERFORMED: NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture – 2013; Fabric Cover Test and UFAC Fabric Classification Test Method – 1990; Standard Test Methods for Cigarette Ignition Resistance of Components of Upholstered Furniture ASTM E 1353-16 – Cover Fabric Test

TEST RESULTS

For the Account of:

Specimen	Char Length (in)		
1	0.5		
2	0.6		
3	0.5		

NOTES

Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity

ACCEPTANCE CRITERIA

- 1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 45 mm (1.75 in; ASTM states 1.8 in.) or less, the fabric is classified a Class I cover fabric.
- 2. If the vertical char of the test specimen greater than 45 mm (1.75 in.; ASTM states 1.8 in), the fabric is classified a Class II cover fabric.
- 3. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a Class II cover fabric.

CONCLUSION	Based on the above Results and Acceptance Criteria, the item tested is:		
	☑ Class I		
	☐ Class II		

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver

Authorized Signature Date Order Completed: 05/20/2024