

Our Ref: LAS/RM

09 August 2024

Report 425474/5.1**Page 1 of 4**

Zimmer & Rohde GmbH
Zimmersmuhlenweg 14-18
61440 Oberursel
Germany

Contact: Matthew Mackenzie

DATE RECEIVED	:	05 AUGUST 2024
DATE TESTED	:	09 AUGUST 2024
QUALITY REFERENCE	:	FR-VELVET
REPUTED FIBRE CONTENT	:	PILE 100% PES FR GROUND 100% PES
COLOUR / DESIGN	:	11009
FABRIC DESCRIPTION	:	WOVEN
END USE	:	UPHOLSTERY
ORDER NUMBER	:	Z + R

REQUEST: BS7176:2007 + A1:2011 Specification for resistance to ignition of upholstered furniture for non-domestic seating by testing composites – Table 1: Medium Hazard Use

RESULT: Meets the flammability performance requirements of Table 1 for Medium Hazard Use



R. MASKILL
FLAMMABILITY TECHNOLOGIST



L. SMITH
QUALITY COORDINATOR

This report shall not be reproduced except in full without written approval of Eurofins MTS Consumer Product Testing UK Limited. In all circumstances results of tests are implied as referring only to the sample supplied and should not be construed or interpreted on any other basis. The comments given in the report are for guidance only and are not a part of the results. Where specified in a test method preconditioning in accordance with ISO 139 is not carried out as samples are exposed to the conditioning atmosphere specified within ISO 139 for a minimum of 16 hours prior to test.



1428

BS 7176:2007 + A1:2011 Specification for resistance to ignition of upholstered furniture for non-domestic seating by testing composites

BS7176:2007 +A1:2011 specifies flammability performance requirements for composites comprising cover fabric and filling material(s) and includes additional requirements in clause 4.1.2 relating to the flammability behavior of the filling materials used. The filling materials which will be used in the final article are not always known to the fabric supplier and therefore nominal filling materials are used for the purpose of testing which may not necessarily represent the final composite. All filling materials supplied for the purpose of testing cover fabrics comply with the relevant requirements of clause 4.1.2.

Clause 4.1.1 requires that testing is carried out in accordance with the frequency stated in clause 5. No information was provided by the client regarding the lot size or frequency of testing.

According to Table 1, composites for Medium Hazard end-use shall meet the requirements of BSEN 1021-1:2006 (cigarette ignition source), BSEN 1021-2:2006 (match-equivalent flame) and BS 5852:2006 Clause 11 (ignition source crib 5).

Pre-treatment:

In accordance with clause 4.2, all fabrics which have been chemically treated to reduce their ignitability are subjected to the water soaking and drying procedures specified in BS 5852:2006 Annex E prior to being conditioned. Such pre-treatment is not necessary for materials which are formulated to be or are inherently flame-retarded.

Pre-treatment applied: None (tested in 'as received' condition)

Conditioning

After any pre-treatment given but prior to testing, the test specimens were subjected to conditioning for at least 72 hours in ambient indoor conditions followed by a minimum of 24 hours at a temperature of (23± 2°C) and relative humidity of (50±5%).

Test results

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use. They also only relate to the materials tested. They do not guarantee to represent the performance of production materials.

Filling material used: As agreed with the client, a combustion modified high resilience foam infill of approximately 35 kg/m³ was used.

- (i) BS EN 1021-1:2006 Furniture - Assessment of the ignitability of upholstered furniture – Part I. Ignition Source: Smouldering cigarette.

<u>Test</u>	<u>Observations</u>	<u>Outcome</u>
1	No flaming or progressive smouldering observed	NI (Non-ignition)
2	No flaming or progressive smouldering observed	NI (Non-ignition)

- (ii) BS EN 1021-2:2006 Furniture - Assessment of the ignitability of upholstered furniture – Part 2. Ignition Source Match flame equivalent.

Duration of flame application: 15 seconds

<u>Test</u>	<u>Observations</u>	<u>Outcome</u>
1	Duration of flaming: 0 secs No progressive smouldering observed	NI (Non-ignition)
2	Duration of flaming: 0 secs No progressive smouldering observed	NI (Non-ignition)
3	Duration of flaming: 0 secs No progressive smouldering observed	NI (Non-ignition)

